

VALORI NOMINALI / NOMINAL VALUES

TEST	UNIT	GSM						STD
Grammatura Basis Weight Valore medio +/-3% Average value	gr/m ²	110	120	130	140	150		ISO 536
Umidità Moisture Valore medio +/-5% Average value	%	7,5	7,5	7,5	7,5	7,5		ISO 287
Scoppio Bursting Strengt Valore medio +/-5% Average value	kPa	220	240	260	280	300		ISO 2758
SCT CD Valore medio +/-5% Average value	KN/m	1.75	1.90	2.05	2.15	2.28		ISO 9895
RCT CD Valore medio +/-5% Average value	KN/m	0.80	0.88	0.95	1.13	1.20		ISO 12192

Colla : Cobb60 < 40 g/m² a richiesta

CARTIERA di RIVALTA SrL - Via Don Cesare Scala, 51
37020 Brentino Belluno (VR)
Tel. +39 045.6284063 - info@cartierarivalta.com



Il marchio della
gestione forestale
responsabile