

### VALORI NOMINALI / NOMINAL VALUES

TEST	UNIT	GSM						STD
<b>Grammatura</b> Basis Weight Valore medio +/-3% Average value	gr/m <sup>2</sup>	110	120	130	140	150		ISO 536
<b>Umidità</b> Moisture Valore medio +/-5% Average value	%	7,5	7,5	7,5	7,5	7,5		ISO 287
<b>Scoppio</b> Bursting Strengt Valore medio +/-5% Average value	kPa	187	204	221	238	255		ISO 2758
<b>SCT CD</b> Valore medio +/-5% Average value	KN/m	1.31	1.45	1.63	1.72	1.84		ISO 9895
<b>RCT CD</b> Valore medio +/-5% Average value	KN/m	0.59	0.70	0.75	0.80	0.92		ISO 12192