

WELLENSTOFF

Rev.08 del 03.02.2023

Grammatura gr/m ²	Umidità %	CMT 30 N	SCT CD kN/m
+/- 3%	+/- 5%	+/- 5%	+/- 5%
100	7	160	1,70
110	7	175	1,85
120	7	190	2,0
130	7	210	2,15
140	7	220	2,30
150	7	230	2,40
160	7	240	2,50
170	7	250	2,60