

TEST LINER 2

Rev.01 del 23.04.2025

Grammatura gr/m ²	Umidità %	RCT kN/m	SCT CD kN/m	Scoppio kPa
+/- 3%	+/- 1	+/- 5%	+/- 5%	+/- 5%
120	8,0	1,10	1,92	306
145	8,0	1,40	2,32	363
175	8,0	1,80	2,70	420
200	8,0	2,10	3,10	480
225	8,0	2,40	3,30	518

Cobb60 = 30

CARTIERA di RIVALTA SrL - Via Don Cesare Scala, 51
37020 Brentino Belluno (VR)
Tel. +39 045.6284063 - info@cartierarivalta.com



Il marchio della
gestione forestale
responsabile