

### VALORI NOMINALI / NOMINAL VALUES

TEST	UNIT	GSM						STD
<b>Grammatura</b> Basis Weight Valore medio +/-3% Average value	gr/m <sup>2</sup>	110	120	130	140	150		ISO 536
<b>Umidità</b> Moisture Valore medio +/-5% Average value	%	7,5	7,5	7,5	7,5	7,5		ISO 287
<b>Scoppio</b> Bursting Strengt Valore medio +/-5% Average value	kPa	220	240	260	280	300		ISO 2758
<b>SCT CD</b> Valore medio +/-5% Average value	KN/m	1.75	1.90	2.05	2.15	2.28		ISO 9895
<b>RCT CD</b> Valore medio +/-5% Average value	KN/m	0.80	0.88	0.95	1.13	1.20		ISO 12192

Colla : Cobb60 < 40 g/m<sup>2</sup> a richiesta

CARTIERA di RIVALTA SrL - Via Don Cesare Scala, 51  
37020 Brentino Belluno (VR)  
Tel. +39 045.6284063 - [info@cartierarivalta.com](mailto:info@cartierarivalta.com)



Il marchio della  
gestione forestale  
responsabile